



HGH®

Micro blasting medium


article-no.	grain size (approx.)	areas of application
SM2000A	15 - 25 µm	Removing the martensitic layer to the fine processing of surfaces below Ra - value of 0.6 µm .
SM2001A	20 - 40 µm	Removing the martensitic layer of the eroded parts, surface RA - value of 0.6 – 1.2 µm .
SM2002A	50 - 70 µm	Removing the martensitic layer of the eroded parts, surface RA - value > 1.2 µm .
SM2915A	90 µm	Preparing an adhesive surface for galvanic coatings. Paint primer. Descaling. Lightweight structure up to 24 VDI .
SM2490A	0,1 - 0,4 mm	Descaling, derusting, matte, finishing. Preparing an adhesive surface for painting. Structuring to VDI 30 .
SM2240A	0,4 - 1,2 mm	Descaling, derusting. Adhesive basic preparation for painting and coating work. Structuring to VDI 33 .
SM2552GT	30 µm	Surface- and anti-stick-compaction in the two-stage blasting process. Preparation for polishing.
SM2001G	70 - 110 µm	Surface compression. Surface finish on medical instruments and devices made of V2A and V4A.
SM2002G	150 - 250 µm	Surface compression. Surface compaction. Creates silky lustre on tools of thermoset, V2A and aluminium.
SM2005K	0,2 - 0,4 mm	Cleaning of screws, cylinders and tools of injection and extrusion devices. Remove of paint and varnish.
SM2006K	0,6 - 0,8 mm	Cleaning of screws, cylinders and tools of injection and extrusion devices. Remove of paint and varnish.
SM2007K	1,0 - 1,6 mm	Cleaning of screws, cylinders and tools of injection and extrusion devices. Remove of paint and varnish.

The packing size is 25 kg = 1 bag.

More micro blasting medium on request



2490A



2002G



2005K

Delivery: from stock Lüdenschheid, subject to prior sale.

If you have questions, we are always available.




Phone: 0049/2351/94757-0 Fax: 0049/2351/94757-67

verkauf@hgh-luedenschheid.de

Stand 2019



hgh-luedenschheid.de

 facebook.com/hghluedenschheid
 xing.com/companies/hghvertriebsgmbh
 linkedin.com/company/hghvertriebsgmbh

HGH®